



| Blade Small | α_w | NRC | SAA | Class |
|----------------------------|------------------------|------------------------|--------------------------|------------------|
| | According to ISO 11654 | According to ASTM C423 | Sound Absorption Average | Sound Absorption |
| On the surface | 0.55 | 0.70 | 0.69 | D |
| Distance to surface: 50mm | 0.70 | 0.90 | 0.88 | C |
| Distance to surface: 100mm | 0.85 | 1.00 | 0.94 | B |

α_s Sound absorption coefficient according to ISO 354

α_p Practical sound absorption coefficient according to ISO 11654