



Hz	α_p
Frequency	Octave
125	0.24
250	0.82
500	0.99
1000	0.85
2000	0.88
4000	1.00

	α_w	NRC	SAA	Class
	According to ISO 11654		According to ASTM C423 Sound Absorption Average	
Cross Drop-In	0.90	0.90	0.92	A

α_s Sound absorption coefficient according to ISO 354

α_p Practical sound absorption coefficient according to ISO 11654