



Hz	$\alpha_p$
Frequency	Octave
125	0.24
250	0.82
500	0.99
1000	0.85
2000	0.88
4000	1.00

	$\alpha_w$	NRC	SAA	Class
	According to ISO 11654		According to ASTM C423 Sound Absorption Average	
<b>Nest-In</b>	<b>0.90</b>	<b>0.90</b>	<b>0.92</b>	<b>A</b>

$\alpha_s$  Sound absorption coefficient according to ISO 354       $\alpha_p$  Practical sound absorption coefficient according to ISO 11654