



**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**
Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar
İstanbul/ TÜRKİYE



TEST REPORT
DENEY RAPORU

AB-0583-T
23007710
04-23

Customer name: HASSAN TEKSTİL SAN VE TİC AŞ
Address: AKÇABURGAZ MAH HADIMKÖY YOLU NO:88 ESENYURT İSTANBUL
Buyer name: -
Contact Person: ÖZGE DÜZGÜN
Order No: -
Article No: 2023-02 N 007 100x50 CM 1 PIECE
Name and identity of test item: One sample of grey panel(Claimed to be;1000 gsm/Grey)
The date of receipt of test item: 28.03.2023
Re-submitted/re-confirmation date: -
Date of test: 28.03.2023-03.04.2023
Remarks: -
Sampling: The results given in this report belong to the received sample by vendor.
End-Use: -
Care Label: -

Number of pages of the report: 3

The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports.

EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş. accredited by TÜRKAK under registration number [AB-0583-T] for ISO 17025:2017 as test laboratory.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.

Seal

Date
03.04.2023

Customer Representative
Zahide TAPAN

Head of Testing Laboratory
Sevim A. RAZAK
03.04.2023

This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.


AB-0583-T

23007710

04-23

REQUIRED TESTS	EVALUATION	COMMENTS
PHYSICAL PROPERTIES TESTS		
Oil Repellency	-	
No requirement was given.		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor $k=2$, providing a level of confidence of approximately 95 %. The declaration of conformity was given in accordance with the Simple Acceptance Decision Rule. (without considering the level of confidence and measurement uncertainty, evaluation of suitability or non-conformity based on whether the test result obtained is only within the specified limits) Tests marked (*) in this report are not included in the accreditation schedule.



This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.

AB-0583-T

23007710

04-23

TEST RESULTS

OIL REPELLENCY; ISO 14419:2010

Performed in the conditioned room ($20 \pm 2^\circ\text{C}$ - $65\% \pm 4$)
Number of test specimens=3 (Approx. 20x20 cm)


RESULT

0 D

REQUIREMENT

-

- A : Passes; clear well-rounded drop
B : Borderline pass; rounding drop with partial darkening
C : Fails; wicking apparent and/or complete wetting
D : Fails; complete wetting



Oil Repellency Grade Number	Composition
0	None
1	White Mineral Oil
2	65:35 White Mineral Oil: n-hexadecan (by volume)
3	n-hexadecan
4	n-tetradecan
5	n-dodecan
6	n-decan
7	n-octan
8	n-heptan

Total uncertainty: $\pm 0,5$ grade