



Hz	α_s	α_p
Frequency	1/3 Octave	Octave
125	0.00	0.03
250	0.10	0.10
500	0.30	0.25
1000	0.50	0.51
2000	0.70	0.73
4000	0.90	0.92

	α_w	NRC	SAA	Class
	According to ISO 11654		According to ASTM C423 Sound Absorption Average	
Onyxa Form	0.30	0.40	0.40	D

α_s Sound absorption coefficient according to ISO 354

α_p Practical sound absorption coefficient according to ISO 11654