



Hz	$\alpha_s$	$\alpha_p$
Frequency	1/3 Octave	Octave
125	0.00	0.02
250	0.10	0.07
500	0.20	0.16
1000	0.40	0.39
2000	0.70	0.66
4000	0.90	0.88

	$\alpha_w$	NRC	SAA	Class
	According to ISO 11654		According to ASTM C423 Sound Absorption Average	
<b>Ridge</b>	0.25	0.30	0.32	E

$\alpha_s$  Sound absorption coefficient according to ISO 354

$\alpha_p$  Practical sound absorption coefficient according to ISO 11654