



**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**  
Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar  
İstanbul/ TÜRKİYE



**TEST REPORT**  
*DENEY RAPORU*

AB-0583-T
23007711
04-23

**Customer name:** HASSAN TEKSTİL SAN VE TİC AŞ  
**Address:** AKÇABURGAZ MAH HADIMKÖY YOLU NO:88 ESENYURT  
İSTANBUL  
**Buyer name:** -  
**Contact Person:** ÖZGE DÜZGÜN  
**Order No:** -  
**Article No:** 2023-02 N 006 100x50 CM 1 PIECE  
**Name and identity of test item:** One sample of grey panel(Claimed to be;1000 gsm/Grey)  
**The date of receipt of test item:** 28.03.2023  
**Re-submitted/re-confirmation date:** -  
**Date of test:** 28.03.2023-03.04.2023  
**Remarks:** -  
**Sampling:** The results given in this report belong to the received sample by vendor.  
**End-Use:** -  
**Care Label:** -

**Number of pages of the report:** 3

*The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports.*

*EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş. accredited by TÜRKAK under registration number [AB-0583-T] for ISO 17025:2017 as test laboratory.*

*The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.*

Seal

Date  
03.04.2023

Customer Representative  
Zahide TAPAN

Head of Testing Laboratory  
Sevim A. RAZAK  
03.04.2023

This report shall not be reproduced other than in full except with the permission of the laboratory.  
*Testing reports without signature and seal are not valid.*



EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.


AB-0583-T

23007711

04-23

REQUIRED TESTS	EVALUATION	COMMENTS
<b>PHYSICAL PROPERTIES TESTS</b>		
Sprey Test	-	
No requirement was given.		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor  $k=2$ , providing a level of confidence of approximately 95 %. The declaration of conformity was given in accordance with the Simple Acceptance Decision Rule. (without considering the level of confidence and measurement uncertainty, evaluation of suitability or non-conformity based on whether the test result obtained is only within the specified limits) Tests marked (\*) in this report are not included in the accreditation schedule.



This report shall not be reproduced other than in full except with the permission of the laboratory.  
*Testing reports without signature and seal are not valid.*



AB-0583-T

23007711

04-23

## TEST RESULTS

### SPRAY TEST; ISO 4920:2012

Performed in the conditioned room (20±2°C-65±4% RH)  
Test was performed original sample.  
Temperature of water 21.3°C.

	<u>RESULT</u>	<u>REQUIREMENT</u>
1.	ISO 0	-
2.	ISO 0	-
3.	ISO 0	-

Toplam belirsizlik:± 0.5 grade

100 ISO 5  
90 ISO 4  
80 ISO 3  
70 ISO 2  
50 ISO 1  
0

### SPRAY RATING SCALE

No sticking or wetting of the specimen face  
Slight random sticking or wetting of the specimen face  
Wetting of specimen face at spray points  
Partial wetting of the specimen face beyond the spray points  
Complete wetting of the entire specimen face beyond the spray points  
Complete wetting of the entire face of the specimen