



Hz	α_s	α_p
Frequency	1/3 Octave	Octave
125	0.00	0.04
250	0.10	0.09
500	0.20	0.25
1000	0.60	0.57
2000	0.80	0.84
4000	1.00	0.99

	α_w	NRC	SAA	Class
	According to ISO 11654		According to ASTM C423 Sound Absorption Average	
Striped Large	0.30	0.50	0.44	D

α_s Sound absorption coefficient according to ISO 354 α_p Practical sound absorption coefficient according to ISO 11654