



Hz	$\alpha_s$
Frequency	1/3 Octave
125	0.05
250	0.12
500	0.29
1000	0.55
2000	0.75
4000	0.97

	$\alpha_w$	NRC	SAA	Class
Reference Product: Bold	According to ISO 11654	According to ASTM C423	Sound Absorption Average	Sound Absorption
<b>Venus</b>	<b>0.35</b>	<b>0.45</b>	<b>0.46</b>	<b>D</b>

$\alpha_s$  Sound absorption coefficient according to ISO 354

$\alpha_p$  Practical sound absorption coefficient according to ISO 11654