



Hz	α_s
Frequency	1/3 Octave
125	0.05
250	0.12
500	0.29
1000	0.55
2000	0.75
4000	0.97

	α_w	NRC	SAA	Class
Reference Product: Bold	According to ISO 11654		According to ASTM C423 Sound Absorption Average	
Zig	0.35	0.45	0.46	D
α_s Sound absorption coefficient according to ISO 354	α_p Practical sound absorption coefficient according to ISO 11654			