

TEST REPORT
DENEY RAPORU

AB-0583-T
23007704
04-23

Müşterinin adı:	HASSAN TEKSTİL SAN VE TİC AŞ
Adresi:	AKÇABURGAZ MAH HADIMKÖY YOLU NO:88 ESENYURT İSTANBUL
Alıcı firma:	-
İlgili kişi:	ÖZGE DÜZGÜN
İstek numarası:	2023-02
Model numarası:	2023-02 N 009 100x50 CM
Numunenin adı ve tarifi:	Gri panel. (Müşteri tarafından belirtilen: 1000 gsm/Gri)
Numunenin kabul tarihi:	28.03.2023
İlave numune ve/veya ilave bilgi geliş tarihi:	-
Deneyin yapıldığı tarih:	28.03.2023-03.04.2023
Açıklamalar:	-
Numune alımı:	Bu raporda verilen sonuçlar müşteri tarafından gönderilen numuneye aittir.
Numunenin son kullanımı:	-
Yıkama talimatı:	Belirtilmedi
Raporun sayfa sayısı:	3
Türk Akreditasyon Kurumu (TÜRKAK) deney raporlarının tanınması konusunda Avrupa Akreditasyon Birliği (EA) ve Uluslararası Laboratuvar Akreditasyon Birliği (ILAC) ile karşılıklı tanınma antlaşmasını imzalamıştır.	
Deney laboratuvarı olarak faaliyet gösteren EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş. TÜRKAK'tan AB-0583-T akreditasyon dosya numarası ile ISO 17025:2017 standardına göre akredite edilmiştir.	
Deney ve/veya ölçüm sonuçları, genişletilmiş ölçüm belirsizlikleri (olması halinde) ve deney metodları bu sertifikanın tamamlayıcı kısmı olan takip eden sayfalarda verilmiştir.	

Mühür

Tarih
03.04.2023

Müşteri Temsilcisi
Zahide TAPAN

Laboratuvar Müdürü
Sevim A. RAZAK
03.04.2023

Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürsüz raporlar geçersizdir.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş**


AB-0583-T

23007704

04-23

İSTENEN TESTLER	DEĞERLENDİRME	AÇIKLAMA
FİZİKSEL TESTLER		
Formaldehit	-	
İstenen değerler müşteri tarafından belirtilmemiştir.		

NOT: Aksi belirtilmediği takdirde testler ile ilgili kayıtlar 5 yıl, orjinal numuneler 3 ay saklanır. Müşteri tarafından talep edildiğinde testlere ait ölçüm belirsizliği raporlanır fakat "Geçer/Kalır" değerlendirmesinde ölçüm belirsizliği değeri dikkate alınmaz. Raporlanan belirsizlik, genişletilmiş belirsizlik olup standart belirsizlik kapsam faktörü $k=2$ kullanılarak elde edilmiştir. Güvenilirlik düzeyi % 95'tir. Uygunluk beyanı Basit Kabul Karar Kuralına (güven düzeyi ve ölçme belirsizliğini göz önünde bulundurmaksızın elde edilen deney sonucunun yalnızca belirtilmiş sınırlar içinde olup olmadığına dayanarak uygunluğun veya uygun olmama durumunun değerlendirilmesi) göre verilmiştir. Bu raporda (*) işaretli deneyler akreditasyon kapsamına dahil değildir



Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürsüz raporlar geçersizdir.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş**

AB-0583-T

23007704

04-23

TEST SONUÇLARI

FORMALDEHİT:ISO 14184-1:2011

Tekstil ürünlerindeki serbest ve likit ekstraksiyonu ile kısmen hidrolize olmuş formaldehit miktarının, su ile ekstraksiyon sonrası kolorimetrik olarak UV-VIS spektrofotometrede 412 nm dalgaboyunda ölçülmesi prensibine dayanır.

	<u>CAS NO</u>	<u>SONUÇ</u>	<u>İSTENEN</u>
Formaldehit	50-00-0	N.D. ⁽¹⁾	-

N.D ⁽¹⁾: <LOD

Toplam belirsizlik:%15,6



EKOTEKS
LABORATUVAR VE GÖZETİM HİZMETLERİ A.Ş.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş**
Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar
İstanbul/ TÜRKİYE



TEST REPORT
DENEY RAPORU

AB-0583-T
23007704- ing
04-23

Customer name: HASSAN TEKSTİL SAN VE TİC AŞ
Address: AKÇABURGAZ MAH HADIMKÖY YOLU NO:88 ESENYURT
İSTANBUL
Buyer name: -
Contact Person: ÖZGE DÜZGÜN
Order No: -
Article No: 2023-02 N 009 100x50 CM
Name and identity of test item: One sample of grey panel(Claimed to be;1000 gsm/Grey)
The date of receipt of test item: 28.03.2023
Re-submitted/re-confirmation date: -
Date of test: 28.03.2023-03.04.2023
Remarks: -
Sampling: The results given in this report belong to the received sample by vendor.
End-Use: -
Care Label: -
Number of pages of the report: 3
The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports.
EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş. accredited by TÜRKAK under registration number [AB-0583-T] for ISO 17025:2017 as test laboratory.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.

Seal

Date
03.04.2023

Customer Representative
Zahide TAPAN

Head of Testing Laboratory
Sevim A. RAZAK
03.04.2023

This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**


AB-0583-T

23007704-
ing

04-23

REQUIRED TESTS	EVALUATION	COMMENTS
PHYSICAL PROPERTIES TESTS		
Formaldehyde	-	
No requirement was given.		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor $k=2$, providing a level of confidence of approximately 95 %. The declaration of conformity was given in accordance with the Simple Acceptance Decision Rule. (without considering the level of confidence and measurement uncertainty, evaluation of suitability or non-conformity based on whether the test result obtained is only within the specified limits) Tests marked (*) in this report are not included in the accreditation schedule.



This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

AB-0583-T

23007704-
ing

04-23

TEST RESULTS

FORMALDEHYDE; ISO 14184-1:2011

Formaldehyde is extracted from a textile sample with distilled water and the amount of formaldehyde released in the water is determined colorimetrically using UV-VIS spectrophotometer at the wavelength of 412 nm.

	<u>CAS NO</u>	<u>RESULT</u>	<u>REQUIREMENT</u>
Formaldehyde	50-00-0	N.D. ⁽¹⁾	-

N.D.⁽¹⁾: <LOD
Total uncertainty: %15,6